

PEEK/CF30

物性表 Property Data

材料性能 Material Properties	条件 Condition	试验方法 Test Method	单位 Unit	PEEK /CF30
机械性能 Mechanical Data				
拉伸强度 Tensile Strength	23℃	ISO 527	MPa	断裂, 260
断裂伸长率 Tensile Elongation	23℃	ISO 527	%	2.5
拉伸模量 Tensile Modulus	23℃	ISO 527	GPa	31.0
弯曲强度 Flexural Strength	23℃	ISO 178	MPa	360
弯曲模量 Flexural Modulus	23℃	ISO 178	GPa	20.0
简支梁冲击强度 Charpy Impact Strength	23℃, 有缺口 Notched 23℃	ISO 179/1eA	KJ×m ⁻²	8.0
热性能 Thermal Data				
熔点 Melting Point		ISO 11357	℃	334
玻璃化温度 Glass Transition		ISO 11357	℃	143
热膨胀系数 Coefficient of Thermal Expansion	温度低于 Tg 平均值 Temperature Below Tg	ISO 11359	ppm×℃ ⁻¹	40
	温度高于 Tg 平均值 Temperature Above Tg	ISO 11359	ppm×℃ ⁻¹	100
热变形温度 Heat Deflection Temperature	1.8MPa	ISO 75	℃	310
导热系数 Thermal Conductivity	23℃	ISO/CD22007-4	W×m ⁻¹ ×℃ ⁻¹	0.95
物理性能 Miscellaneous				
密度 Density	结晶 Crystalline	ISO 1183	g×cm ⁻³	1.4
熔体粘度 Melting Index	400℃, 1000s ⁻¹	ISO 11443	Pa·s	630
邵氏硬度 Shore D Hardness	23℃	ISO 868	D	87
吸水率 Water Absorption	24h, 23℃	ISO 62-1	%	0.4
表面电阻率 Surface Resistivity	23℃	GB/T 31838.3	Ω	--

体积电阻率 Volume Resistivity	23℃	IEC 60093	Ωcm	--
电气强度 Dielectrical Strength	23℃	IEC 60243-1	kv/mm	--
成型收缩率 Mould Shrinkage Rate	平行流动	ISO 294-4	‰	2
	垂直流动	ISO 294-4	‰	3
摩擦系数 Friction Coefficient	1MPa, 0.7m/s	ASTM G132-96		--
磨损值 Friction Loss	1MPa, 0.7m/s	ASTM G132-96	mm ³ /N·m	--
易燃性等级 Flammability Rating		UL 94		V-0